

## Formaldehyde emission according to Japanese Agricultural Standard for plywood JAS MAFF 233



<b>Desiccators</b>	(10 ± 1) L, glass
<b>Sample specimen size</b>	10 x (150 x 50) mm
<b>Edge sealing</b>	No edge sealing
<b>Temperature</b>	(20 ± 1) °C
<b>Conditioning</b>	Air-tightly sealed in a vinyl bag at (20±1) °C for more than 1 day
<b>Test duration</b>	24 hours ± 10 min
<b>Limit of quantification</b>	0.05 mg/L