

## Formaldehyde emission from wood flooring according to the European chamber method EN 14342



<b>Chambers</b>	225 L, stainless steel
<b>Loading factor</b>	1,0 m <sup>2</sup> per m <sup>3</sup> chamber volume
<b>Sample specimen size</b>	4 x (200 x 280) mm 2 pieces are assembled back-to-back
<b>Edge sealing</b>	Fully edge sealed using aluminum tape
<b>Temperature</b>	(23,0 ± 0,5) °C
<b>Humidity</b>	(45 ± 3) % RH
<b>Air exchange</b>	1/hour
<b>Conditioning</b>	No
<b>Test duration</b>	Until steady state, minimum 10, maximum 28 days
<b>Limit of quantification</b>	0,003 mg/m <sup>3</sup>