

Formaldehyde emission according to Japanese Agricultural Standard for plywood JAS MAFF 233



| | |
|--------------------------------|--|
| Desiccators | (10 ± 1) L, glass |
| Sample specimen size | 10 x (150 x 50) mm |
| Edge sealing | No edge sealing |
| Temperature | (20 ± 1) °C |
| Conditioning | Air-tightly sealed in a vinyl bag at (20±1) °C for more than 1 day |
| Test duration | 24 hours ± 10 min |
| Limit of quantification | 0.05 mg/L |