


Formaldehyde emission from glued laminate timber according to the Japanese chamber test JAS MAFF 235



Chambers	40 L, acrylic
Loading factor	450 cm ² exposed area / 40 L
Sample specimen size	1 x (103 x 103 x 109) mm or other dimensions that fulfill the requirements above
Edge sealing	The butt ends of the specimen shall be sealed with aluminum tape
Temperature	(20 ± 1) °C
Conditioning	Air-tightly sealed in a vinyl bag at (20±1) °C for least 1 day
Test duration	24 hours -0 / +5 min
Limit of quantification	0.05 mg/L