

## Formaldehyde emission according to Japanese Agricultural Standard for Flooring JAS MAFF 240



|                                |  |
|--------------------------------|--|
| <b>Desiccators</b>             | (10 ± 1) L, glass  |
| <b>Sample specimen size</b>    | 10 x (150 x 50) mm   |
| <b>Edge sealing</b>            | No edge sealing  |
| <b>Temperature</b>             | (20 ± 1) °C  |
| <b>Conditioning</b>            | Air-tightly sealed in a vinyl bag at (20±1) °C for more than 1 day |
| <b>Test duration</b>           | 24 hours ± 10 min  |
| <b>Limit of quantification</b> | 0.05 mg/L  |