


Formaldehyde emission from wood-based panels according to the gas analysis method ISO 12460-3



Chamber	4 L, stainless steel
Sample specimen size	3 x (400 x 50) mm
Edge sealing	Fully edge sealed using aluminum tape
Temperature	(60.0 ± 0.5) °C
Air exchange	60 L/hour
Conditioning	Hermetically sealed at ambient temperature °C for at least 1 day
Test duration	4 hours
Limit of quantification	0.2 mg/m ² h